

GC20T standard sections are manufactured from 58 strips of HDPE, resulting in a section length of 29 cells and 21 cells wide. Each strip is the appropriate width and 300 inches (7.62m) in length. Weld spacing is 14.0 in ± 0.12 in. (355 ± 3mm). Cell density is 34.6 cells per meter squared. Cell walls are textured and if perforations are required 13% ± 3% of the cell wall is removed. Polyethylene strip shall be textured and with a multitude of rhomboidal (diamond shape) indentations. The rhomboidal indentations shall have a surface density of 22 to 31 per cm² (140 to 200 per in²).

Color: Standard strips are black. (Tan, Green, other colors with no heavy metal content available upon request)
Stabilizer: Hindered amine light stabilizer (HALS) 2.0% by weight of carrier

MATERIAL PROPERTIES

Description	Test Method	Units	Test Value
> Polymer Density	ASTM D 1505	lb/ft ³ (g/cm ³)	58.4-60.2 (0.935-0.965)
> Environmental Stress Crack Resistance	ASTM D 5397	hours	>400
> Carbon Black Content	ASTM D 1603	% by weight	1.5% minimum
> Nominal Sheet Thickness ⁽¹⁾ before texturing	ASTM D 5199	mil (mm)	50 (1.27) -5%, +10%
> Nominal Sheet Thickness ⁽¹⁾ after texturing	ASTM D 5199	mil (mm)	(1.52) -5%, +10%

PHYSICAL PROPERTIES

Description	Unit	Test Value
> Nominal - Expanded Cell Size Length x Width	in (mm)	8.8 (224) x 10.2 (259)
> Nominal - Expanded Cell Area	in ² (cm ²)	44.8 (289)
> Nominal - Expanded Panel Size (width x length)	ft (m)	17.85 (5.44) x 21.4 (6.52)
> Nominal - Expanded Panel Area	ft ² (m ²)	382 (35.5)

> Cell Depth	in (mm)	2 (50)	3 (75)	4 (100)	6 (150)	8 (200)
> Seam Peel Strength	lbf (N)	160 (710)	240 (1065)	320 (1420)	480 (2130)	640 (2840)
> Seam Hang Strength	A 4 in (102mm) weld joint supporting a load of 160 lbs (72.5 kg) for 30 days minimum or a 4 in (102mm) weld joint supporting a load of 160 lbs (72.5 kg) for 7 days minimum while undergoing temperature change from 74° F (23° C) to 130° F (54° C) on a 1 hour cycle.					



Industrial Fabrics, Inc.
 510 O' Neal Lane Ext
 Baton Rouge, LA 70819
 800 848 4500

BASELOK™ GEOCELL may change product specifications without notice. The determination of whether the BASELOK™ GEOCELL system is suitable for use in the application described in our literature and on our website is to be determined solely by the user. The information provided is not intended to be nor does it represent engineering advice for any particular project or use. Professional engineering should be consulted before installation of BASELOK™ GEOCELL units to assure proper design and installation. ALL EXPRESSED OR IMPLIED WARRANTIES, INCLUDING THOSE OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE ARE DISCLAIMED. BASELOK™ GEOCELL is a trademark of Industrial Fabrics, Inc.