

Product Name:	MUX100
Product Type:	Integrally Formed Uniaxial Geogrid
Polymer:	Polypropylene
Load Transfer Mechanism:	Positive Mechanical Interlock
Primary Applications:	Marine Systems

PRODUCT PROPERTIES¹

Index Properties	Test Method	Units	MD Values ¹	XMD Values ¹
» Aperture Dimensions		in (mm)	5.8 (147)	.6 (15)
» Minimum Rib Thickness ²		in (mm)	.028 (.71)	.028 (.71)
» Percent Open Area ²		%	60	60
» True 1% Tensile Modulus in Use	ASTM D6637	lb/ft (kN/m)	51,400 (750)	51,400 (750)

Structural Integrity

» Junction Strength	ASTM D6637 & D7737	lb/ft (kN/m)	3,330 (48.6)
» Flexural Stiffness	ASTM D7748	mg-cm	700

Durability

» Resistance to Long Term Degradation	EPA 9090	%	100
» Resistance to UV Degradation	ASTM D4355	%	98

Dimensions

	Length ft (m)	Width ft (m)
» *Standard Roll Sizes	250 (76.2)	4.36 (1.33)

***Roll Sizes Depend on Availability at Time of Order**

Dimensions & Delivery

The uniaxial geogrid shall be delivered to the job site in roll form with each roll individually identified and nominally measuring 1.33m (4.36 FT) in width and 76.2m (250 FT) in length.

Notes:

1. Unless indicated otherwise, values shown are Minimum Average Roll Values (MARV) in accordance with ASTM D4759.
2. Nominal dimensions.



Industrial Fabrics, Inc.
510 O'Neal Lane Ext
Baton Rouge LA 70819
800 848 4500
www.baselok.com

BASELOK™ MARINE may change product specifications without notice. The determination of whether the BASELOK™ MARINE system is suitable for use in the application described in our literature and on our website is to be determined solely by the user. The information provided is not intended to be nor does it represent engineering advice for any particular project or use. Professional engineering should be consulted before installation of BASELOK™ MARINE units to assure proper design and installation. ALL EXPRESSED OR IMPLIED WARRANTIES, INCLUDING THOSE OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE ARE DISCLAIMED. BASELOK™ is a trademark of Industrial Fabrics, Inc.